



# Standard Specification for Electric-Fusion-Welded Austenitic Chromium-Nickel Stainless Steel Pipe for High-Temperature Service and General Applications<sup>1</sup>

This standard is issued under the fixed designation A358/A358M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers electric-fusion-welded austenitic chromium-nickel stainless steel pipe suitable for corrosive or high-temperature service, or both, or for general applications.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.2 This specification covers the grades of alloy and stainless steel listed in **Table 1**. The selection of the proper grade and requirements for heat treatment shall be at the discretion of the purchaser, dependent on the service conditions to be encountered.

1.3 Five classes of pipe are covered as follows:

1.3.1 *Class 1*—Pipe shall be double welded by processes employing filler metal in all passes and shall be completely radiographed.

1.3.2 *Class 2*—Pipe shall be double welded by processes employing filler metal in all passes. No radiography is required.

1.3.3 *Class 3*—Pipe shall be single welded by processes employing filler metal in all passes and shall be completely radiographed.

1.3.4 *Class 4*—Same as Class 3 except that the weld pass exposed to the inside pipe surface may be made without the addition of filler metal (see **6.2.2.1** and **6.2.2.2**).

1.3.5 *Class 5*—Pipe shall be double welded by processes employing filler metal in all passes and shall be spot radiographed.

1.4 Supplementary requirements covering provisions ranging from additional testing to formalized procedures for

manufacturing practice are provided. Supplementary Requirements S1 through S6 are included as options to be specified when desired.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

**A240/A240M** Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**A262** Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

**A480/A480M** Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

**A941** Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

**A999/A999M** Specification for General Requirements for Alloy and Stainless Steel Pipe

**E527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 1952. Last previous edition approved in 2015 as A358/A358M – 15. DOI: 10.1520/A0358\_A0358M-19.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specifications SA-358 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.



TABLE 1 Plate and Filler Metal Specifications

Grade	Filler Metal Classification and UNS Designation <sup>A</sup> for Applicable <sup>B</sup> AWS Specification											
	A5.4/A5.4M		A5.9/A5.9M		A5.11/A5.11M		A5.14/A5.14M		A5.22/A5.22M		A5.30/A5.30M	
	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS
...	...	...	...	...	...	...	...	...	...	...	...	...
...	...	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...
...	...	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...
800 <sup>F</sup>	...	...	...	...	...	ENiCrFe-3	W86182	ERNiCr-3	N06082	...	...	...
800H <sup>F</sup>	...	...	...	...	...	ENiCrFe-3 <sup>F</sup>	W86182 <sup>F</sup>	ERNiCr-3 <sup>F</sup>	N06082 <sup>F</sup>	...	...	...
...	...	...	...	...	...	ENiCrFe-3 <sup>F</sup>	W86182 <sup>F</sup>	ERNiCr-3 <sup>F</sup>	N06082 <sup>F</sup>	...	...	...
...	...	...	...	...	...	...	...	...	...	...	...	...
201	...	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...
201LN	...	...	...	...	...	...	...	...	...	...	...	...
...	...	...	...	...	...	...	...	...	...	...	...	...
XM-19	E 209	W32210	ER209	S20980	...	...	...	...	...	...	...	...
XM-29	E209	W32210	ER209	S20980	...	...	...	...	...	...	...	...
304	E240	W32410	ER240	S24080	...	...	...	...	...	...	...	...
304L	E308	W30810	ER308	S30880	...	...	...	...	E308T	W30831	IN308	S30880
304H	E308L	W30813	ER308L	S30883	...	...	...	...	E308LT	W30835	IN308L	S30883
...	E308H	W30810	ER308	S30880	...	...	...	...	E308T	W30831	IN308	S30880
...	...	...	...	...	...	...	...	...	...	...	...	...
304N	E308	W30810	ER308	S30880	...	...	...	...	E308T	W30831	IN308	S30880
304LN	E308L	W30813	ER308L	S30883	...	...	...	...	E308LTT	W30835	IN308L	S30883
...	...	...	...	...	...	...	...	...	...	...	...	...
309S	...	...	...	...	...	...	...	...	...	...	...	...
309Cb	E309Cb	W30917	...	...	...	...	...	...	...	...	...	...
310S	...	...	...	...	...	...	...	...	...	...	...	...
310Cb	E310Nb	W31017	...	...	...	...	...	...	...	...	...	...
...	...	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...
...	...	...	...	...	...	ENiCrMo-13	W86059	ERNiCrMo-13	N06059	...	...	...



TABLE 1 Continued

Grade	Filler Metal Classification and UNS Designation <sup>A</sup> for Applicable <sup>B</sup> AWS Specification											
	A5.4/A5.4M		A5.9/A5.9M		A5.11/A5.11M		A5.14/A5.14M		A5.22/A5.22M		A5.30/A5.30M	
	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS	Class.	UNS
...	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	E316	W31610	ER316	ER316	ENiCrMo-10	W86022	ERNiCrMo-10	N06022	E316T	W31631	IN316	S31680
A240/A240M	E316L	W31613	ER316L	ER316L	...	...	...	...	E316LT	W31635	IN316L	S31683
A240/A240M	E316H	W31610	ER316H	ER316H	...	...	...	...	E316T	W31631	IN316	S31680
A240/A240M	E316	W31610	ER316	ER316	...	...	...	...	E316T	W31631	IN316	S31680
A240/A240M	E316L	W31613	ER316L	ER316L	...	...	...	...	E316LT	W31635	IN316L	S31683
...	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	E317	W31710	ER 317	ER 317	...	...	...	...	E317LT	W31735	...	...
A240/A240M	E317L	W34713	ER317L	ER317L	...	...	...	...	E317LT	W31735	...	...
...	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...	...
A240/A240M	...	...	...	...	ENiCrMo-3	W86112	ERNiCrMo-3	N06625	...	...	...	...
...	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	E347	W34710	ER321	ER321	...	...	...	...	E347T	W34731	IN348	S34780
A240/A240M	...	...	ER347	ER347	...	...	...	...	E347T	W34731	IN348	S34780
A240/A240M	...	...	ER321	ER321	...	...	...	...	...	...	...	...
A240/A240M	...	...	ER347	ER347	...	...	...	...	...	...	...	...
...	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	E347	W34710	ER347	ER347	...	...	...	...	E347T	W34731	IN348	S34780
A240/A240M	...	...	ER347	ER347	...	...	...	...	E347T	W34731	IN348	S34780
...	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	...	...	...	...	...	...	...	...	...	...	...	...
A240/A240M	E347	W34710	ER347	ER347	...	...	...	...	E347T	W34731	IN348	S34780

<sup>A</sup> New designation established in accordance with Practice E527 and SAE J1086.

<sup>B</sup> Choice of American Welding Society specification depends on the welding process used.

<sup>C</sup> Minimum carbon content of the filler metal shall be 0.040 mass %.

<sup>D</sup> In previous editions, S30600 was incorrectly shown as S01815.

<sup>E</sup> Common name, not a trademark, widely used, not associated with any one producer.

<sup>F</sup> These filler metals have a high nickel content and, therefore, lower creep strength than the parent metal at temperatures exceeding about 1470 °F [800 °C], and its resistance to sulphurous media is inferior in certain cases.



2.2 ASME Boiler and Pressure Vessel Code:<sup>4</sup>

Section II

Section III

Section VIII

Section IX

2.3 AWS Specifications:<sup>5</sup>

A5.4/A5.4M Stainless Steel Electrodes for Shielded Metal Arc Welding

A5.9/A5.9M Bare Stainless Steel Welding Electrodes and Rods

A5.11/A5.11M Nickel and Nickel-Alloy Welding Electrodes for Shielded Metal Arc Welding

A5.14/A5.14M Nickel and Nickel-Alloy Bare Welding Electrodes and Rods

A5.22/A5.22M Stainless Steel Flux Cored and Metal Cored Welding Electrodes and Rods

A5.30/A5.30M Consumable Inserts

2.4 Other Standard:<sup>6</sup>

SAE J1086 Practice for Numbering Metals and Alloys (UNS)

### 3. Terminology

3.1 Definitions:

3.1.1 The definitions in Specification A999/A999M and Terminology A941 are applicable to this specification.

### 4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for product under this specification. Such requirements to be considered include, but are not limited to, the following:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Name of material (electric-fusion-welded pipe),

4.1.3 Grade (Table 1),

4.1.4 Class (see 1.3),

4.1.5 Size (outside diameter and nominal wall thickness),

4.1.6 Length (specific or random),

4.1.7 End finish (Section on Ends of Specification A999/A999M),

4.1.8 Authorization for repair of plate defects by welding and subsequent heat treatment without prior approval if such is intended (see 9.3),

4.1.9 Specification designation,

4.1.10 Special requirements,

4.1.11 Statement invoking requirements of 16.4 if such is intended.

4.1.12 Circumferential weld permissibility (see Section 16),

4.1.13 Supplementary Requirements (S1 through S8),

4.1.14 Applicable ASME Code if known,

4.1.15 For ASME Code Section III applications, the service classification intended, and

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

<sup>5</sup> Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

<sup>6</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

4.1.16 Certification requirements (see Section on Certification of Specification A999/A999M).

### 5. General Requirements

5.1 Material furnished to this specification shall conform to the applicable requirements of the current edition of Specification A999/A999M unless otherwise provided herein.

### 6. Materials and Manufacture

6.1 Materials:

6.1.1 The steel plate material shall conform to the requirements of one of the grades of Specification A240/A240M, listed in Table 1, except as provided in 6.3.2.3.

6.2 Welding:

6.2.1 The joints shall be full penetration double-welded or single-welded butt joints employing fusion welding processes as defined under "Definitions," ASME Boiler and Pressure Vessel Code, Section IX. This specification makes no provision for any difference in weld quality requirements regardless of the weld joint type employed (single or double) in making the weld. Where backing rings or strips are employed, the ring or strip material shall be of the same P-Number (Table QW-422 of Section IX) as the plate being joined. Backing rings or strips shall be completely removed after welding, prior to any required radiography, and the exposed weld surface shall be examined visually for conformance to the requirements of 6.2.3. Welds made by procedures employing backing strips or rings that remain in place are prohibited. Welding procedures, and welding operators shall be qualified in accordance with ASME Boiler and Pressure Vessel Code, Section IX.

6.2.2 Except as provided in 6.2.2.1 and 6.2.2.2, welds shall be made in their entirety by processes involving the deposition of filler metal.

6.2.2.1 For Class 4 pipe employing multiple passes, the root-pass may be without the addition of filler metal.

6.2.2.2 For Class 4 pipe, the weld surface exposed inside the pipe may result from a single pass made from the inside of the pipe without the addition of filler metal.

6.2.2.3 All single-welded pipe shall be completely radiographed.

6.2.3 The weld surface on either side of the weld is permitted to be flush with the base plate or to have a reasonably uniform crown, not to exceed 1/8 in. [3 mm]. It is permitted at the option of the manufacturer or by agreement between the manufacturer and purchaser to remove any weld reinforcement. The contour of the reinforcement should be reasonably smooth and free from irregularities. The deposited metal shall be fused uniformly into the plate surface. No concavity of contour is permitted unless the resulting thickness of weld metal is equal to or greater than the minimum thickness of the adjacent base metal.

6.2.4 Weld defects shall be repaired by removal to sound metal and rewelding. Subsequent heat treatment and examination (that is, visual, radiographic, and dye penetrant) shall be as required on the original welds.

6.3 Heat Treatment:



6.3.1 Unless otherwise stated in the order, all pipe shall be furnished in the heat-treated condition in accordance with the requirements of **Table 2**.

6.3.2 The purchase order shall specify one of the following conditions if the heat-treated condition specified in 6.3.1 is not desired by the purchaser:

6.3.2.1 *A final heat-treatment temperature under 1900 °F [1040 °C]*—Each pipe supplied under this requirement shall be stenciled with the final heat-treatment temperature in degrees Fahrenheit or degrees Celsius after the suffix “HT.” Controlled structural or special service characteristics may be specified as a guide for the most suitable heat treatment.

6.3.2.2 *No final heat treatment of pipe fabricated of plate that has been solution heat treated at temperatures required by this specification*—Each pipe supplied under this requirement shall be stenciled with the suffix “HT-O.”

6.3.2.3 *No final heat treatment of pipe fabricated of plate that has not been solution heat treated*—Each pipe supplied under this requirement shall be stenciled with the suffix “HT-SO.”

6.4 A solution annealing temperature above 1950 °F [1065 °C] may impair the resistance to intergranular corrosion after subsequent exposure to sensitizing conditions in Grades 321, 321H, 347, 347H, and 348. When specified by the purchaser, a lower temperature stabilization or re-solution anneal shall be used subsequent to the initial high temperature solution anneal (see Supplementary Requirement S5).

**7. Chemical Composition**

7.1 The chemical composition of the plate shall conform to the requirements of the applicable specification and grade listed in Specification **A240/A240M**.

7.2 Except for Grade S34751 and S34752, the chemical composition of the welding filler metal shall conform to the requirements of the applicable AWS specification for the corresponding grade shown in **Table 1**, or shall conform to the chemical composition specified for the plate in Specification **A240/A240M**, or shall, subject to purchaser approval, be a filler metal more highly alloyed than the base metal when needed for corrosion resistance or other properties. Use of a filler metal other than that listed in **Table 1** or conforming to the chemical composition specified for the plate in Specification **A240/A240M** shall be reported and the filler metal identified on the certificate of tests. When nitrogen and cerium are specified elements for the ordered grade, the method of analysis for these elements shall be a matter of agreement between the purchaser and the manufacturer.

7.3 The chemical composition of the welding filler metal for Grade S34751 and S34752 shall conform to the chemical composition specified for the plate in Specification **A240/A240M**. The method for analysis for nitrogen shall be a matter of agreement between the purchaser and the manufacturer.

**8. Permissible Variations in Dimensions**

8.1 *Permissible Variations*—The dimensions at any point in a length of pipe shall not exceed the following:

8.1.1 *Outside Diameter*—Based on circumferential measurement, ±0.5 % of the specified outside diameter.

8.1.2 *Out-of-Roundness*—Difference between major and minor outside diameters, 1 %.

8.1.3 *Alignment*—Using a 10-ft [3-m] straightedge placed so that both ends are in contact with the pipe, 1/8 in. [3 mm] deviation from contact with the pipe.

**TABLE 2 Annealing Requirements**

Grade or UNS Designation <sup>A</sup>	Heat Treating Temperature <sup>B</sup>	Cooling/Testing Requirements
All grades not individually listed below:	1900 °F [1040 °C]	C
304H, 309S, 309Cb, 310S, 310Cb, 321H, 347H, S22100, S28300,	1900 °F [1040 °C]	D
N08020	1800-1850 °F [980-1010 °C]	D
N08367	2025 °F [1110 °C]	D
N08700	2000 °F [1095 °C]	D
N08810	2050 °F [1120 °C]	D
N08811	2100 °F [1150 °C]	D
N08904	2000 °F [1095 °C]	D
N08926	2010 °F [1100 °C]	D
S30600	2100 °F [1150 °C]	D
S30815	1920 °F [1050 °C]	D
S31254	2100 °F [1150 °C]	D
S31266	2100 °F [1150 °C]	D
S31727	1975-2175 °F [1080 to 1180 °C]	D
S32050	2100 °F [1150 °C]	D
S32053	1975-2175 °F [1080 to 1180 °C]	D
S32654	2100 °F [1150 °C]	D
S34565	2050 °F [1120 °C]	D
S34752	1940-2138 °F [1060 to 1170 °C]	D

<sup>A</sup> New designation established in accordance with Practice **E527** and SAE J1086.

<sup>B</sup> Minimum, unless otherwise stated.

<sup>C</sup> Quenched in water or rapidly cooled by other means, at a rate sufficient to prevent reprecipitation of carbides, as demonstrable by the capability of passing Practices **A262**, Practice E. The manufacturer is not required to run the test unless it is specified on the purchase order (see Supplementary Requirement S7). Note that Practices **A262** requires the test to be performed on sensitized specimens in the low-carbon and stabilized types and on specimens representative of the as-shipped condition for other types. In the case of low-carbon types containing 3 % or more molybdenum, the applicability of the sensitizing treatment prior to testing shall be a matter of negotiation between the seller and the purchaser.

<sup>D</sup> Quenched in water or rapidly cooled by other means.

8.1.4 *Thickness*—The minimum wall thickness at any point in the pipe shall not be more than 0.01 in. [0.3 mm] under the nominal thickness.

## 9. Workmanship, Finish, and Appearance

9.1 The finished pipe shall have a workmanlike finish.

9.2 *Repair of Plate Defects by Machining or Grinding*—It is permitted to repair pipes showing slivers, or other surface defects, by machining or grinding inside or outside to a depth that ensures the removal of all included scale and slivers, provided that the wall thickness is not reduced below the specified minimum wall thickness. Machining or grinding shall follow inspection of the pipe as rolled, and shall be followed by supplementary visual inspection.

9.3 *Repair of Plate Defects by Welding*—It is permitted to repair by welding defects that violate minimum wall thickness, but only with the approval of the purchaser. Areas shall be suitably prepared for welding with tightly closed defects removed by grinding. Open, clean defects, such as pits or impressions, may require no preparation. All welders, welding operators, and weld procedures shall be qualified to the ASME Boiler and Pressure Vessel Code, Section IX. Unless the purchaser specifies otherwise, pipe required to be heat treated under the provisions of 6.3, shall be heat treated or reheat treated following repair welding. Repaired lengths, where repair depth is greater than 1/4 of the thickness, shall be pressure tested or repressure tested after repair and heat treatment (if any). Repair welds shall also be examined by suitable non-destructive examination techniques, including any techniques specifically required of the primary weld.

9.4 The pipe shall be free of scale and contaminating iron particles. Pickling, blasting, or surface finishing is not mandatory when pipe is bright annealed. The purchaser is permitted to request that a passivating treatment be applied.

## 10. Heat Analysis

10.1 An analysis of each heat of steel shall be made by the plate manufacturer to determine the percentages of the elements prescribed in Specification A240/A240M. The chemical composition thus determined shall conform to the requirements prescribed in Specification A240/A240M.

## 11. Product Analysis

11.1 For each lot of 500 ft [150 m] of pipe or fraction thereof, analysis shall be made by the manufacturer from the finished pipe of the plate and of the weld deposit. Drillings for analysis may be taken from the mechanical test specimens. The results of these analyses shall be reported to the purchaser or the purchaser's representative, and shall conform to the requirements of Section 7, subject to the product analysis tolerances of Table 1 in Specification A480/A480M.

11.2 If the analysis of one of the tests specified in 9.1 does not conform to the requirements specified in Section 7, analyses shall be made on additional pipe of double the original number from the same lot, each of which shall conform to the requirements specified.

## 12. Tensile Requirements

12.1 The plate used in making the pipe shall conform to the requirements as to tensile properties of the applicable specifications listed in Table 1. Tension tests made by the plate manufacturer shall qualify the plate material.

12.2 The transverse tension test taken across the welded joint specimen shall have a tensile strength not less than the specified minimum tensile strength of the plate.

## 13. Transverse Guided-Bend Weld Tests

13.1 Two bend test specimens shall be taken transversely from the pipe. Except as provided in 13.2, one shall be subject to a face guided-bend test and the second to a root guided-bend test. One specimen shall be bent with the inside surface of the pipe against the plunger, and the other with the outside surface against the plunger.

13.2 For wall thicknesses over 3/8 in. [9.5 mm] but less than 3/4 in. [19 mm] side-bend tests may be made instead of the face and root-bend tests. For specified wall thicknesses 3/4 in. [19 mm] and over, both specimens shall be subjected to the side-bend tests. Side-bend specimens shall be bent so that one of the side surfaces becomes the convex surface of the bend specimen.

13.3 The bend test shall be acceptable if no cracks or other defects exceeding 1/8 in. [3 mm] in any direction is present in the weld metal or between the weld and the pipe metal after bending. Cracks that originate along the edges of the specimen during testing, and that are less than 1/4 in. [6.5 mm] measured in any direction shall not be considered.

## 14. Test Specimens and Methods of Testing

14.1 Transverse tension and bend test specimens shall be taken from the end of the finished pipe; the transverse tension and bend test specimens shall be flattened cold before final machining to size.

14.2 As an alternative to the requirements of 14.1, it is permitted to take the test specimens from a test plate of the same material as the pipe that is attached to the end of the cylinder and welded as a prolongation of the pipe longitudinal seam.

14.3 Tension test specimens shall be made in accordance with Section IX, Part QW, Paragraph QW-150 of the ASME Boiler and Pressure Vessel Code and shall be one of the types shown in QW-462.1 of that code.

14.3.1 Reduced-section specimens conforming to the requirements given in QW-462.1(b) may be used for tension tests on all thicknesses of pipe having outside diameter greater than 3 in. [76 mm].

14.3.2 Turned specimens conforming to the requirements of QW-462.1(d) may be used for tension tests.

14.3.2.1 If turned specimens are used as given in 14.3.2.2 and 14.3.2.3, one complete set shall be made for each required tension test.

14.3.2.2 For thicknesses to and including 1 1/4 in. [32 mm], it is permitted to use a single turned specimen.

14.3.2.3 For thicknesses over 1 1/4 in. [32 mm], multiple specimens shall be cut through the full thickness of the weld



deposit chemistry; testing equipment and method; number and location of test sites; and ferrite control limits) shall be a matter for agreement between the purchaser and the manufacturer.

### **S5. Stabilizing Heat Treatment**

S5.1 Subsequent to the heat treatment required in 6.3, Grades 321, 321H, 347, 347H, and 348 shall be given a stabilization heat treatment at a temperature lower than that used for the initial solution annealing heat treatment. The temperature of stabilization heat treatment shall be at a temperature as agreed upon between the purchaser and manufacturer.

### **S6. Intergranular Corrosion Test**

S6.1 When specified, material shall pass intergranular corrosion tests conducted by the manufacturer in accordance with Practices A262, Practice E.

NOTE S1—Practice E requires testing on the sensitized condition for low carbon or stabilized grades, and on the as-shipped condition for other grades.

S6.2 A stabilization heat treatment in accordance with Supplementary Requirement S5 may be necessary and is permitted in order to meet this requirement for the grades containing titanium or columbium.

### **S7. In-Process Heat Treatments**

S7.1 For H grades, separate solution treatments are required for solution annealing. In-process heat treatments are not permitted as a substitute for separate solution annealing.

### **S8. ASME Section III or Section VIII, Division 1, Construction**

S8.1 Products furnished under this specification that are intended for application under the rules of Section III or Section VIII, Division 1, of the ASME Boiler and Pressure

Vessel Code shall be manufactured by holders of the appropriate ASME Certificate of Authorization and Certification Mark. The product is subject to all applicable requirements of Section III or Section VIII, Division 1, including welding, heat treatment, nondestructive examination, authorized inspection at the point of manufacture, and application of the Certification Mark.

S8.2 The applicable ASME Partial Data Report form, signed by an Authorized Inspector or Authorized Nuclear Inspector and a material test report shall be furnished for each lot of pipe.

S8.3 The welded joints shall be full penetration butt welds as obtained by double welding or by other means that will obtain the same quality of deposited weld metal on the inside and outside. Welds using metal backing strips that remain in place are prohibited.

S8.4 In addition to the requirements of 15.1, for pipe that is not heat treated, or that is heat treated in a continuous furnace, a lot shall consist of each 200 ft [60 m] or fraction thereof, of all pipe of the same heat of plate starting material of the same thickness, subjected to the same heat treatment. For pipe that is heat treated in a batch-type furnace that is automatically controlled within a 50 °F [25 °C] range and is equipped with recording pyrometers so that the heating records are available, a lot shall be defined as for continuous furnace heat treatment. Each length of pipe shall be so marked as to identify each such piece of pipe with the lot and the material test report.

## **SUMMARY OF CHANGES**

Committee A01 has identified the location of selected changes to this standard since the last issue, A358/A358M – 15, that may impact the use of this standard. (Approved Nov. 1, 2019.)

- (1) Added new alloy to Table 1 as S34752.
- (2) Added alloy to heat treatment to Table 2.

- (3) Added comments in 7.2 and 7.3 on the welding filler metal.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*