



Designation: B622 – 23

## Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube<sup>1</sup>

This standard is issued under the fixed designation B622; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification<sup>2</sup> covers seamless pipe and tube of nickel and nickel-cobalt alloys. covers seamless pipe and tube of nickel and nickel-cobalt alloys.

1.2 Alloys that can currently be certified to this specification are (UNS N10001, UNS N10242, UNS N10665, UNS N12160, UNS N10675, UNS N10276, UNS N06455, UNS N06007, UNS N08320, UNS N06975, UNS N06002, UNS N06985, UNS N06022, UNS N06035, UNS N06044, UNS N08135, UNS N06255, UNS N06058, UNS N06059, UNS N06200, UNS N10362, UNS N06030, UNS N08031, UNS N08034, UNS R30556, UNS N08535, UNS N06250, UNS N06060, UNS N06230, UNS N06235, UNS N06686, UNS N10629, UNS N06210, UNS N10624, and UNS R20033)<sup>3</sup>.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Dec. 1, 2023. Published December 2023. Originally approved in 1977. Last previous edition approved in 2017 as B622 – 17b. DOI: 10.1520/B0622-23.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SB-622 in Section II of that Code.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>4</sup>

**B829** Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

**B899** Terminology Relating to Non-ferrous Metals and Alloys

**E8/E8M** Test Methods for Tension Testing of Metallic Materials

**E527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

### 3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this specification, refer to Terminology **B899**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *average diameter, n*—the average of the maximum and minimum outside diameters, or the maximum and minimum inside diameters, as determined at any cross section of the tube.

3.2.2 *pipe, n*—seamless tube conforming to the particular dimensions commercially known as standard pipe sizes (**Appendix X2**).

3.2.3 *tube, n*—a hollow product of round or any other cross section having a continuous periphery.

### 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of Specification **B829** unless otherwise provided herein.

### 5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the material ordered under this specification. Examples of such requirements include, but are not limited to the following:

5.1.1 *Alloy* (**Table 1**).

5.1.2 *Dimensions:*

<sup>4</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Chemical Requirements<sup>A</sup>**

		Composition Limits, %																					
		W	C	Si	Co	Mn	V	P <sub>max</sub>	S <sub>max</sub>	Ti	Cu	Cb (Nb) + Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+Mo	Mg		
Ni-Mo Alloys	N10001	...	0.05	1.0	2.5	1.0	0.2-0.4	0.04	0.03	...	...	...	...	...	...	...	...	...	...	...	...	...	
	N10665	...	0.02	0.10	1.0	1.0	...	0.04	0.03	...	...	...	...	...	...	...	...	...	...	...	...	...	
	N10675	3.0	0.01	0.10	3.0	3.0	0.20	0.030	0.010	0.20	0.20	...	0.50	0.10	...	...	...	0.20	0.20	94.0-98.0	...	...	
	N10629	...	0.01	0.05	2.5	1.5	...	0.04	0.01	...	0.5	...	0.1-0.5	...	...	...	...	...	...	...	...	...	...
	N10624	...	0.01	0.10	1.0	1.0	...	0.025	0.01	...	0.5	...	...	...	...	...	...	...	...	...	...	...	...
Ni-Mo-Cr-Fe Alloy	N10242	2.0	0.03	0.80	1.00	0.80	0.030	0.015	0.015	0.50	0.50	0.006	0.50	...	...	...	...	...	...	...	...	...	
	Low C Ni-Cr-Mo Alloys	...	0.010	0.08	2.5	1.0	0.35	0.04	0.03	...	...	...	...	...	...	...	...	...	...	...	...	...	
Ni-Cr-Fe-Mo-Cu Alloys	N06007	1.0	0.05	1.0	2.5	1.0-2.0	...	0.04	0.03	...	1.5-2.5	1.75-2.5	...	...	...	...	...	...	...	...	...	...	
	N06975	...	0.03	1.0	...	1.0	...	0.03	0.03	0.70-1.50	0.70-1.20	...	...	...	...	...	...	...	...	...	...	...	
	N06985	1.5	0.015	1.0	5.0	1.0	...	0.04	0.03	...	1.5-2.5	0.50	...	...	...	...	...	...	...	...	...	...	
	N06030	13.0-17.0	0.03	0.8	5.0	1.5	...	0.04	0.02	...	1.0-2.4	0.30-1.50	...	...	...	...	...	...	...	...	...	...	
	N06255	remainder	0.03	1.0	...	1.0	...	0.03	0.03	0.69	1.2	...	...	...	...	...	...	...	...	...	...	...	
	N06250	remainder	0.020	0.09	...	...	1.00	...	0.005	...	0.25-1.25	...	...	...	...	...	...	...	...	...	...	...	
	Ni-Fe-Cr-Mo Alloys	...	0.05	1.0	...	...	2.5	...	0.03	0.03	4xC min	...	...	...	...	...	...	...	...	...	...	...	
	N08320	remainder	0.05	1.0	...	...	2.5	...	0.04	0.03	...	...	...	...	...	...	...	...	...	...	...	...	
	N08135	remainder	0.030	0.75	...	...	1.00	...	0.03	0.03	...	...	...	...	...	...	...	...	...	...	...	...	
	Ni-Cr-Fe-Mo Alloys	0.20-0.80	0.030	0.75	...	...	1.00	...	0.03	0.03	...	...	...	...	...	...	...	...	...	...	...	...	

**TABLE 1 Continued**

		Composition Limits, %																							
		Ni	Cr	Mo	Fe	W	C	Si	Co	Mn	V	P <sub>max</sub>	S <sub>max</sub>	Ti	Cu	Cb (Nb) + Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+Mo	Mg
N06002		remainder	20.5-23.0	8.0-10.0	17.0-20.0	0.20-1.0	0.05-0.15	1.0	0.5-2.5	1.0	...	0.04	0.03	...	...	...	...	...	...	...	...	...	...	...	...
N06060		54.0-60.0	19.0-22.0	12.0-14.0	remainder	0.25-1.25	0.03	0.50	...	1.50	...	0.030	0.005	...	0.25-1.25	0.50-1.25	...	...	...	...	...	...	...	...	...
Ni-Cr-Mo-Cu Alloy		remainder	30.0-32.5	5.0-6.2	1.5	0.60	0.02-0.06	0.2-0.6	1.0	0.3-0.65	...	0.03	0.015	0.5	3.5-4.0	...	0.2-0.4	...	...	...	...	...	...	...	...
Ni-Fe-Cr-Co Alloy		19.0-22.5	21.0-23.0	2.5-4.0	remainder	2.0-3.5	0.05-0.15	0.20-0.80	16.0-21.0	0.50-2.00	...	0.04	0.015	...	...	...	0.10-0.50	0.001-0.10	0.005-0.10	0.10-0.30	0.02	0.30-1.25	...	...	
Ni-Cr-W-Mo Alloys		remainder	20.0-24.0	1.0-3.0	3.0	13.0-15.0	0.05-0.15	0.25-0.75	5.0	0.30-1.00	...	0.03	0.015	...	...	...	0.50	...	0.005-0.050	...	0.015	...	...	...	
Low C-Ni-Cr-Mo-Cu Alloy		remainder	22.0-24.0	15.0-17.0	3.0	...	0.010	0.08	2.0	0.50	...	0.025	0.010	...	1.3-1.9	...	0.50	...	...	...	...	...	...	...	
Low C-Ni-Mo-Cr Alloy		remainder	13.8-15.6	21.5-23.0	1.25	...	0.010	0.08	...	0.60	...	0.025	0.010	...	...	...	0.50	...	...	...	...	...	...	...	
Low C-Ni-Fe-Cr-Mo-Cu Alloys		30.0-32.0	26.0-28.0	6.0-7.0	balance	...	0.015	0.3	...	2.0	...	0.020	0.010	...	1.0-1.4	...	...	...	...	0.15-0.25	...	...	...	...	
N08031		33.5-35.0	26.0-27.0	6.0-7.0	balance	...	0.01	0.1	...	1.0-4.0	...	0.020	0.010	...	0.5-1.5	...	0.3	...	...	0.10-0.25	...	...	...	...	
N08034		29.0-36.5	24.0-27.0	2.5-4.0	remainder	...	0.03	0.50	...	1.0	...	0.03	0.03	...	1.50	...	...	...	...	...	...	...	...	...	
N08535		remainder	19.0-23.0	15.0-17.0	5.0	3.0-4.4	0.010	0.08	...	0.75	...	0.04	0.02	0.02-0.25	...	...	...	...	...	...	...	...	...	...	
Low C-Ni-Cr-Mo-W Alloy		remainder	26.0-30.0	1.0 max	3.5	1.0	0.15	2.4-3.0	27.0-33.0	1.5	...	0.030	0.015	0.20-0.80	...	...	...	...	...	...	...	...	...	...	
Ni-Co-Cr-Si Alloy		remainder	31.0-35.0	0.50-2.0	balance	...	0.015	0.50	...	2.0	...	0.02	0.01	...	0.3-1.20	...	...	...	...	0.35-0.60	...	...	...	...	
N12160		remainder	26.0-30.0	1.0 max	3.5	1.0	0.15	2.4-3.0	27.0-33.0	1.5	...	0.030	0.015	0.20-0.80	...	...	...	...	...	...	...	...	...	...	
Cr-Ni-Fe-N Alloy		30.0-33.0	31.0-35.0	0.50-2.0	balance	...	0.015	0.50	...	2.0	...	0.02	0.01	...	0.3-1.20	...	...	...	...	...	...	...	...	...	

**TABLE 1 Continued**

		Composition Limits, %																							
		Ni	Cr	Mo	Fe	W	C	Si	Co	Mn	V	P <sub>max</sub>	S <sub>max</sub>	Ti	Cu	Cb (Nb) + Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+ Mo	Mg
Low C-Ni-Mo-Cr-Ta Alloy N06210		remainder	18.0-20.0	18.0-20.0	1.0	...	0.015	0.08	1.0	0.5	0.35	0.02	0.02	...		...		...	...	...	...	...	1.5-2.2		

<sup>A</sup> Values in the table are maximums unless a range or minimum is indicated.

5.1.2.1 *Tube*—Outside diameter, minimum or average wall thickness, and length.

5.1.2.2 *Pipe*—Standard pipe size and schedule (Appendix X2).

5.1.3 *Ends*—Plain ends cut and deburred will be furnished.

5.1.4 *Certification*—State if certification or a report of test results is required (Section 16).

5.1.5 *Samples for Check Analysis*—State whether samples for check analysis should be furnished.

5.1.6 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state, indicating which tests or inspections are to be witnessed (Section 15).

## 6. Materials and Manufacture

6.1 Products certified to this specification shall have been manufactured in accordance with Specification B829.

6.2 Products certified to this specification shall be supplied in the solution annealed and descaled condition. When atmosphere control is used, descaling is not necessary.

## 7. Chemical Composition

7.1 The material shall conform to the composition limits specified in Table 1.

7.2 If a product (check) analysis is made by the purchaser, the material shall conform to the requirements specified in Table 1 subject to the permissible tolerances in accordance with Specification B829.

## 8. Mechanical Properties

8.1 The mechanical properties of the material at room temperature shall conform to those shown in Table 2.

## 9. Hydrostatic Test or Non-Destructive Electric Test

9.1 Each pipe or tube shall be tested by the manufacturer by either hydrostatic or a non-destructive electric test in accordance with Specification B829. Hydrostatic testing at a pressure greater than 1000 psi may be performed upon agreement between the purchaser and manufacturer or at the option of the manufacturer provided that the allowable fiber stress per Specification B829 is not exceeded.

## 10. Dimensions and Weight

### 10.1 Diameter:

10.1.1 This specification is limited to tubes up to and including 3.5 in. (88.9 mm) outside diameter.

10.2 *Weight*—For calculation of mass or weight, the following densities shall be used:

TABLE 2 Mechanical Properties of Pipe and Tube

Alloy	Tensile Strength, min, ksi (MPa)	Yield Strength (0.2 % Offset) min, ksi (MPa)	Elongation in 2 in. (50.8 mm) or 4D, <sup>A</sup> min, %
Ni-Mo			
UNS N10001	100 (690)	45 (310)	40
UNS N10665	110 (760)	51 (350)	40
UNS N10675	110 (760)	51 (350)	40
UNS N10629	110 (760)	51 (350)	40
UNS N10624	104 (720)	46 (320)	40
Ni-Mo-Cr-Fe			
UNS N10242	105 (725)	45 (310)	40
Low C Ni-Cr-Mo			
UNS N10276	100 (690)	41 (283)	40
UNS N06022	100 (690)	45 (310)	45
UNS N06035	85 (586)	35 (241)	30
UNS N06044	100 (690)	45 (310)	30
UNS N06455	100 (690)	40 (276)	40
Ni-Cr-Fe-Mo-Cu			
UNS N06007	90 (621)	35 (241)	35
UNS N06975	85 (586)	32 (221)	40
UNS N06985	90 (621)	35 (241)	40
UNS N06030	85 (586)	35 (241)	30
UNS N06255	85 (586)	32 (221)	40
UNS N06250	90 (621)	35 (241)	40
Ni-Fe-Cr-Mo			
UNS N08320	75 (517)	28 (193)	35
UNS N08135	73 (503)	31 (214)	40
Ni-Cr-Mo-Fe			
UNS N06002	100 (690)	40 (276)	35
UNS N06060	90 (621)	35 (241)	40
Ni-Cr-Mo-Cu			
UNS N06235	90 (620)	35 (240)	35
Ni-Fe-Cr-Co			
UNS R30556	100 (690)	45 (310)	40
Ni-Cr-W-Mo			
UNS N06230 <sup>B</sup>	110 (760)	45 (310)	40
Low C-Ni-Cr-Mo			
UNS N06058	110 (760)	52 (360)	40
UNS N06059	100 (690)	45 (310)	45
Low C-Ni-Cr-Mo-Cu			
UNS N06200	100 (690)	45 (310)	45
Low C-Ni-Mo-Cr			
UNS N10362	105 (725)	45 (310)	40
Ni-Fe-Cr-Mo-Cu low carbon			
UNS N08031	94 (650)	40 (276)	40
UNS N08034	94 (650)	40 (280)	40
UNS N08535	73 (503)	31 (214)	40
Low C Ni-Cr-Mo-W			
UNS N06686	100 (690)	45 (310)	45
Ni-Co-Cr-Si			
UNS N12160	90 (620)	35 (240)	40
low carbon Cr-Ni-Fe-N			
UNS R20033	109 (750)	55 (380)	40
Low carbon Ni-Mo-Cr-Ta			
UNS N06210	100 (690)	45 (310)	45

<sup>A</sup> D refers to the diameter of the tension specimen.

<sup>B</sup> Solution annealed at a minimum temperature of 2200 °F (1204 °C) followed by a water quench or rapidly cooled by other means.

Alloy	Density	
	lb/in. <sup>3</sup>	g/cm <sup>3</sup>
Nickel-molybdenum:		
UNS N10001	0.334	9.24
UNS N10242	0.327	9.05
UNS N10665	0.333	9.22
UNS N10675	0.333	9.22
UNS N10629	0.333	9.22
UNS N10624	0.322	8.9
Low carbon nickel-chromium-molybdenum:		
UNS N10276	0.321	8.87
UNS N06022	0.314	8.69
UNS N06035	0.296	8.18
UNS N06044	0.287	7.97
UNS N06455	0.312	8.64
Nickel-chromium-iron-molybdenum-copper:		
UNS N06007	0.300	8.31
UNS N06975	0.295	8.17
UNS N06985	0.300	8.31
UNS N06030	0.297	8.22
UNS N06255	0.299	8.29
UNS N06250	0.307	8.58
Nickel-iron-chromium-molybdenum:		
UNS N08320	0.291	8.05
UNS N08135	0.292	8.10
Nickel-chromium-molybdenum-iron:		
UNS N06002	0.297	8.23
UNS N06060	0.315	8.71
Nickel-chromium-molybdenum-copper:		
UNS N06235	0.295	8.16
Nickel-iron-chromium-cobalt:		
UNS R30556	0.297	8.23
Nickel-chromium-tungsten-molybdenum:		
UNS N06230	0.324	8.97
Low carbon nickel-chromium-molybdenum:		
UNS N06058	0.318	8.80
UNS N06059	0.311	8.6
UNS N06200	0.307	8.50
Low carbon-nickel-molybdenum-chromium:		
UNS N10362	0.319	8.83
Low carbon nickel-iron-chromium-molybdenum-copper:		
UNS N08031	0.29	8.1
UNS N08034	0.293	8.10
UNS N08535	0.291	8.07
Low carbon nickel-chromium-molybdenum-tungsten:		
UNS N06686	0.315	8.73
Nickel-cobalt-chromium-silicon:		
UNS N12160	0.292	8.08
Low carbon chromium-nickel-iron-nitrogen:		
UNS R20033	0.29	8.1
Low carbon nickel-molybdenum-chromium-tantalum:		
UNS N06210	0.316	8.76

## 11. Sampling

11.1 *Lots for Chemical Analysis and Mechanical Testing are as defined in Specification B829.*

11.2 *Sampling of Chemical Analysis:*

11.2.1 A representative sample shall be taken from each lot during pouring or subsequent processing.

11.2.2 Product (check) analysis shall be wholly the responsibility of the purchaser.

11.3 *Sampling for Mechanical Testing:*

11.3.1 A representative sample shall be taken from each lot of finished material.

## 12. Number of Tests and Retests

12.1 *Chemical Analysis*—One test per lot.

12.2 *Tension Test*—One test per lot.

12.3 *Retests*—If the specimen used in the mechanical test of any lot fails to meet the specified requirements, two additional specimens shall be taken from different sample pieces and tested. The results of the tests on both of these specimens shall meet the specified requirements.

## 13. Specimen Preparation

13.1 Tension test specimens shall be taken from material after final heat treatment and tested in the direction of fabrication.

13.2 Whenever possible, all pipe and tube shall be tested in full tubular size. When testing in full tubular size is not possible, longitudinal strip specimens, or the largest possible round specimen prepared in accordance with Test Methods E8/E8M, shall be used.

## 14. Test Methods

14.1 The chemical composition and mechanical properties of the material as enumerated in this specification shall be determined in accordance with the methods in Specification B829.

## 15. Inspection

15.1 Inspection of the material shall be in accordance with this specification and agreements between the manufacturer and the purchaser as part of the purchase contract.

## 16. Certification

16.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

## 17. Keywords

17.1 seamless pipe; seamless tube; UNS N06002; UNS N06007; UNS N06022; UNS N06030; UNS N06035; UNS N06044; UNS N06058; UNS N06059; UNS N06060; UNS N06200; UNS N06210; UNS N06230; UNS N06235; UNS N06250; UNS N06255; UNS N06455; UNS N06686; UNS N06975; UNS N06985; UNS N08031; UNS N08034; UNS N08135; UNS N08320; UNS N08535; UNS N10001; UNS N10242; UNS N10276; UNS N10362; UNS N10624; UNS N10629; UNS N10665; UNS N10675; UNS N12160; UNS R20033; UNS R30556

APPENDIXES

(Nonmandatory Information)

X1. HEAT TREATMENT

X1.1 Proper heat treatment during or subsequent to fabrication is necessary for optimum performance and the manufacturer shall be consulted for details.

X2. PIPE SCHEDULES

TABLE X2.1 Pipe Schedules<sup>A</sup>

Nominal Pipe Size, in.	Outside Diameter	Nominal Wall Thickness		
		Schedule No. 10	Schedule No. 40	Schedule No. 80
		Inches		
1/4	0.540	0.065	0.088	...
3/8	0.675	0.065	0.091	0.126
1/2	0.840	0.083	0.109	0.147
3/4	1.050	0.083	0.113	0.154
1	1.315	0.109	0.133	0.179
1 1/4	1.660	0.109	0.140	0.191
1 1/2	1.900	0.109	0.145	0.200
2	2.375	0.109	0.154	0.218
2 1/2	2.875	0.120	0.203	0.276
3	3.500	0.120	0.216	0.300
		Millimetres		
1/4	13.72	1.65	2.24	...
3/8	17.14	1.65	2.31	3.20
1/2	21.34	2.11	2.77	3.73
3/4	26.67	2.11	2.87	3.91
1	33.40	2.77	3.38	4.55
1 1/4	42.16	2.77	3.56	4.85
1 1/2	48.26	2.77	3.68	5.08
2	60.32	2.77	3.91	5.54
2 1/2	73.02	3.05	5.16	7.04
3	88.90	3.05	5.49	7.62

<sup>A</sup> The pipe schedules shown conform with standards adopted by the American National Standards Institute.

X2.1 The schedules listed in Table X2.1 are regularly available. This table is published for information only.

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B622 – 17b) that may impact the use of this standard. (Approved December 1, 2023.)

- (1) Updated Section 1.
- (2) Added alloy N06235 to Section 1.
- (3) Updated Table 1 and Table 2.
- (4) Revised Section 3 and Section 10.
- (5) Added Section 6.
- (6) Revised Keywords.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*