

English Version

Aluminium and aluminium alloys - Extruded rod/bar, tube and profiles - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Barres, tubes et
profilés filés - Partie 2 : Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen -
Stranggepresste Stangen, Rohre und Profile - Teil 2:
Mechanische Eigenschaften

This European Standard was approved by CEN on 10 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
European foreword.....		3
1	Scope	4
2	Normative references	4
3	Mechanical property limits	4
3.1	General.....	4
3.2	Elongation	4
3.3	Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys.....	5
3.4	Tables of mechanical properties	7
Annex A (informative) List of tempers used in Tables 1 to 61 (extract of EN 515)		56
Bibliography.....		58

European foreword

This document (EN 755-2:2016) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 755-2:2013.

CEN/TC 132 decided to revise EN 755-2:2013 as follows:

- reorganization of the list of the tables of mechanical properties of the relevant aluminium and aluminium alloys;
- addition of the alloy EN AW-2618A [AlCu₂Mg_{1,5}Ni] in a new Table 9;
- correction of the alloy EN AW-6026 [Al MgSiBi] in a new Table 36;
- addition of the alloy EN AW-6056 [Al Si₁MgCuMn] in a new Table 38.
- Modification of the Alloy EN AW-6060 [Al MgSi] in Table 39: Extruded profile T6 and T66 wall thickness-border from 3 mm to 5 mm;
- Modification of the Alloy EN AW-6063 [Al Mg_{0,7}Si] in Table 45: Extruded profile T5 wall thickness-border from 3 mm to 10 mm;
- The former Table 26 was moved, and is now Table 48.

EN 755, *Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles* comprises the following parts:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*
- *Part 9: Profiles, tolerances on dimensions and form*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy extruded rod/bar, tube and profile.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 755-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 755-1, *Aluminium and aluminium alloys- Extruded rod/bar, tube and profiles - Part 1: Technical conditions for inspection and delivery*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

3 Mechanical property limits

3.1 General

The mechanical properties shall be in conformity with those specified in Table 1 to Table 61 or those agreed upon between supplier and purchaser and stated in the order document.

Table 1 to Table 61 contain limits of mechanical property values obtained by tensile testing according to EN ISO 6892-1 after sampling and test piece preparation according to EN 755-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Table 1 to Table 61 expressed as HBW values are for information only.

3.2 Elongation

If not otherwise agreed, the A value shall be used.

The A value for elongation is the % elongation measured over a gauge length of $5,65\sqrt{S_0}$ (where S_0 is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on A_{50mm} . Consequently, values for the A_{50mm} are included in the following tables.

The A_{50mm} value is the elongation measured over a gauge length of 50 mm and expressed in percent.

Test pieces and their location in the specimen are given in EN 755-1.

3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys

			Page
Table 1	Aluminium EN AW-1050A	[Al 99,5]	7
Table 2	Aluminium EN AW-1070A	[Al 99,7]	7
Table 3	Aluminium EN AW-1200	[Al 99,0]	8
Table 4	Aluminium EN AW-1350	[Al 99,5]	8
Table 5	Alloy EN AW-2007	[Al Cu ₄ PbMgMn]	9
Table 6	Alloy EN AW-2011 and EN AW-2011A	[Al Cu ₆ BiPb] and [Al Cu ₆ BiPb(A)]	9
Table 7	Alloy EN AW-2014 and EN AW-2014A	[Al Cu ₄ SiMg] and [Al Cu ₄ SiMg(A)]	10
Table 8	Alloy EN AW-2017A	[Al Cu ₄ MgSi(A)]	11
Table 9	Alloy EN AW-2618A	[AlCu ₂ Mg _{1,5} Ni]	12
Table 10	Alloy EN AW-2024	[Al Cu ₄ Mg ₁]	13
Table 11	Alloy EN AW-2030	[Al Cu ₄ PbMg]	14
Table 12	Alloy EN AW-3102	[Al Mn _{0,2}]	15
Table 13	Alloy EN AW-3003	[Al Mn ₁ Cu]	16
Table 14	Alloy EN AW-3103	[Al Mn ₁]	17
Table 15	Alloy EN AW-5005 and EN AW-5005A	[Al Mg ₁ (B)] and [Al Mg 1(C)]	18
Table 16	Alloy EN AW-5019	[Al Mg ₅]	19
Table 17	Alloy EN AW-5049	[Al Mg ₂ Mn _{0,8}]	20
Table 18	Alloy EN AW-5051A	[Al Mg ₂]	20
Table 19	Alloy EN AW-5251	[Al Mg ₂ Mn _{0,3}]	21
Table 20	Alloy EN AW-5052	[Al Mg _{2,5}]	22
Table 21	Alloy EN AW-5154A	[Al Mg _{3,5} (A)]	23
Table 22	Alloy EN AW-5454	[Al Mg ₃ Mn]	24
Table 23	Alloy EN AW-5754	[Al Mg ₃]	25
Table 24	Alloy EN AW-5083	[Al Mg _{4,5} Mn _{0,7}]	26
Table 25	Alloy EN AW-5086	[Al Mg ₄]	27
Table 26	Alloy EN AW-6101A	[Al MgSi(A)]	27
Table 27	Alloy EN AW-6101B	[Al MgSi(B)]	28
Table 28	Alloy EN AW-6005 and EN AW-6005A	[Al SiMg] and [Al SiMg(A)]	29
Table 29	Alloy EN AW-6106	[Al MgSiMn]	30
Table 30	Alloy EN AW-6008	[Al SiMgV]	30
Table 31	Alloy EN AW-6110A	[Al Mg _{0,9} Si _{0,9} MnCu(A)]	31
Table 32	Alloy EN AW-6012	[Al MgSiPb]	32

			Page
Table 33	Alloy EN AW-6014	[Al Mg0,6SiV]	33
Table 34	Alloy EN AW-6018	[Al Mg1SiPbMn]	34
Table 35	Alloy EN AW-6023	[Al Si1Sn1MgBi]	34
Table 36	Alloy EN AW-6026	[Al MgSiBi]	35
Table 37	Alloy EN AW-6351	[Al Si1Mg0,5Mn]	36
Table 38	Alloy EN AW-6056	[Al Si1MgCuMn]	37
Table 39	Alloy EN AW-6060	[Al MgSi]	38
Table 40	Alloy EN AW-6360	[Al SiMgMn]	39
Table 41	Alloy EN AW-6061	[Al Mg1SiCu]	40
Table 42	Alloy EN AW-6261	[Al Mg1SiCuMn]	41
Table 43	Alloy EN AW-6262	[Al Mg1SiPb]	42
Table 44	Alloy EN AW-6262A	[Al Mg1SiSn]	42
Table 45	Alloy EN AW-6063	[Al Mg0,7Si]	43
Table 46	Alloy EN AW-6063A	[Al Mg0,7Si(A)]	44
Table 47	Alloy EN AW-6463	[Al Mg0,7Si(B)]	45
Table 48	Alloy EN AW-6064A	[Al Mg1SiBi]	46
Table 49	Alloy EN AW-6065	[Al Mg1Bi1Si]	46
Table 50	Alloy EN AW-6081	[Al Si0,9MgMn]	47
Table 51	Alloy EN AW-6082	[Al Si1MgMn]	48
Table 52	Alloy EN AW-6182	[Al Si1MgZr]	49
Table 53	Alloy EN AW-7003	[Al Zn6Mg0,8Zr]	49
Table 54	Alloy EN AW-7005	[Al Zn4,5Mg1,5Mn]	50
Table 55	Alloy EN-AW-7108	[Al Zn5Mg1Zr]	50
Table 56	Alloy EN-AW-7108A	[Al Zn5Mg1Zr(A)]	51
Table 57	Alloy EN AW-7020	[Al Zn4,5Mg1]	52
Table 58	Alloy EN AW-7021	[Al Zn5,5Mg1,5]	52
Table 59	Alloy EN AW-7022	[Al Zn5Mg3Cu]	53
Table 60	Alloy EN AW-7049A	[Al Zn8MgCu]	54
Table 61	Alloy EN AW-7075	[Al Zn5,5MgCu]	55

3.4 Tables of mechanical properties

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	60	-	20	-	25	23	20
O, H111	all	all	60	95	20	-	25	23	20
Extruded tube									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min	
F ^c , H112	all		60		20	-	25	23	20
O, H111	all		60	95	20	-	25	23	20
Extruded profile									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min	
F ^c , H112	all		60		20	-	25	23	20
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 2 — Aluminium EN AW-1070A [Al 99,7]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	60	-	23		25	23	18
Extruded tube									
Not specified									
Extruded profile									
Not specified									
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 3 — Aluminium EN AW-1200 [Al 99,0]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	75	-	25	-	20	18	23
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	75	-	25		20	18	23
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		75	-	25		20	18	23
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 4 — Aluminium EN AW-1350 [Al 99,5]

Extruded rod/bar ^d									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	60	-	-	-	25	23	20
Extruded tube ^d									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		60	-	-	-	25	23	20
Extruded profile ^d									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		60	-	-	-	25	23	20
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									
^d Electrical conductivity $\gamma \geq 35,4$ MS/m.									

Table 5 — Alloy EN AW-2007 [Al Cu4PbMgMn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 ^c	≤ 80	≤ 80	370	-	250	-	8	6	95
	$80 < D \leq 200$	$80 < S \leq 200$	340	-	220	-	8	-	
	$200 < D \leq 250$	$200 < S \leq 250$	330	-	210	-	7	-	
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 ^c	≤ 25		370	-	250	-	8	6	95
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 ^c	≤ 30		370	-	250	-	8	6	95
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 6 — Alloy EN AW-2011 [Al Cu6BiPb] and Alloy EN AW-2011A [Al Cu6BiPb(A)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 200	≤ 60	275	-	125	-	14	12	95
T6 ^c	≤ 75	≤ 60	310	-	230	-	8	6	110
	$75 < D \leq 200$	-	295	-	195	-	6	-	110
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 25		310	-	230	-	6	4	110
Extruded profile									
Not specified									
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 7 — Alloy EN AW-2014 [Al Cu4SiMg] and Alloy EN AW-2014A [Al Cu4SiMg(A)]

Drawn rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	250	-	135	12	10	45
T4, T4510, T4511	≤ 25	≤ 25	370	-	230	-	13	11	110
	$25 < D \leq 75$	$25 < S \leq 75$	410	-	270	-	12	-	110
	$75 < D \leq 150$	$75 < S \leq 150$	390	-	250	-	10	-	110
	$150 < D \leq 200$	$150 < S \leq 200$	350	-	230	-	8	-	110
T6, T6510, T6511	≤ 25	≤ 25	415	-	370	-	6	5	140
	$25 < D \leq 75$	$25 < S \leq 75$	460	-	415	-	7	-	140
	$75 < D \leq 150$	$75 < S \leq 150$	465	-	420	-	7	-	140
	$150 < D \leq 200$	$150 < S \leq 200$	430	-	350	-	6	-	140
	$200 < D \leq 250$	$200 < S \leq 250$	420	-	320	-	5	-	140
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			min.	max.	min.	max.	% min.	% min.	
O, H111		≤ 20	-	250	-	135	12	10	45
T4, T4510, T4511		≤ 20	370	-	230	-	11	10	110
T6, T6510, T6511		≤ 10	415	-	370	-	7	5	140
		$10 < t \leq 40$	450	-	400	-	6	4	140
Extruded profile ^c									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			min.	max.	min.	max.	% min.	% min.	
O, H111		all	-	250	-	135	12	10	45
T4, T4510, T4511		≤ 25	370	-	230	-	11	10	110
		$25 < t \leq 75$	410	-	270	-	10	-	110
T6, T6510, T6511		≤ 25	415	-	370	-	7	5	140
		$25 < t \leq 75$	460	-	415	-	7	-	
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c If a profile cross section comprises different thicknesses which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 8 — Alloy EN AW-2017A [Al Cu4MgSi(A)]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	250	-	135	12	10	45
T4, T4510, T4511 ^c	≤ 25	≤ 25	380	-	260	-	12	10	105
	$25 < D \leq 75$	$25 < S \leq 75$	400	-	270	-	10	-	105
	$75 < D \leq 150$	$75 < S \leq 150$	390	-	260	-	9	-	105
	$150 < D \leq 200$	$150 < S \leq 200$	370	-	240	-	8	-	105
	$200 < D \leq 250$	$200 < S \leq 250$	360	-	220	-	7	-	105
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 20	-	250	-	135	12	10	45
T4, T4510, T4511 ^c		≤ 10	380	-	260	-	12	10	105
		$10 < t \leq 75$	400	-	270	-	10	8	105
Extruded profile									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 ^c		≤ 30	380	-	260	-	10	8	105
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 9 — Alloy EN AW-2618A [Al Cu2Mg1.5Ni]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T6, T6511	$D \leq 10$	$S \leq 10$	410	-	330	-	6	4	140
T6, T6511	$10 < D \leq 100$	$10 < S \leq 100$	420	-	360	-	7	5	145
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
			min.	max.	min.	max.			
T6, T6511		≤ 10	410	-	330	-	6	4	140
T6, T6511		$10 < t \leq 100$	420	-	360	-	7	5	145
Extruded profile ^c									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
			min.	max.	min.	max.			
T6, T6511		≤ 10	410	-	330	-	6	4	140
T6, T6511		$10 < t \leq 100$	420	-	360	-	7	5	145
^a D = Diameter for round bar.									
^b Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 10 — Alloy EN AW-2024 [Al Cu4Mg1]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	250	-	150	12	10	47
T3, T3510, T3511	≤ 50	≤ 50	450	-	310	-	8	6	120
	$50 < D \leq 100$	$50 < S \leq 100$	440	-	300	-	8	-	120
	$100 < D \leq 200$	$100 < S \leq 200$	420	-	280	-	8	-	120
	$200 < D \leq 250$	$200 < S \leq 250$	400	-	270	-	8	-	120
T8, T8510, T8511	≤ 150	≤ 150	455	-	380	-	5	4	130
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 30	-	250	-	150	12	10	47
T3, T3510, T3511		≤ 30	420	-	290	-	8	6	120
T8, T8510, T8511		≤ 30	455	-	380	-	5	4	130
Extruded profile ^c									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
O, H111		all	-	250	-	150	12	10	47
T3, T3510, T3511		≤ 15	395	-	290	-	8	6	120
		$15 < t \leq 50$	420	-	290	-	8	-	120
T8, T8510, T8511		≤ 50	455	-	380	-	5	4	130
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 11 — Alloy EN AW-2030 [Al Cu4PbMg]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T4, T4510, T4511 ^c	≤ 80	≤ 80	370	-	250	-	8	6	115
	$80 < D \leq 200$	$80 < S \leq 200$	340	-	220	-	8	-	115
	$200 < D \leq 250$	$200 < S \leq 250$	330	-	210	-	7	-	115
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T4, T4510, T4511 ^c		≤ 25	370	-	250	-	8	6	115
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T4, T4510, T4511 ^c		≤ 30	370	-	250	-	8	6	115
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 12 — Alloy EN AW-3102 [Al Mn0,2]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
F ^c , H112	all	all	80	-	30	-	25	23	23
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112		all	80	-	30	-	25	23	23
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112		all	80	-	30	-	25	23	23
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 13 — Alloy EN AW-3003 [Al Mn1Cu]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
F ^c , H112	all	all	95	-	35	-	25	20	30
O, H111	all	all	95	135	35	-	25	20	30
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112	all		95	-	35	-	25	20	30
O, H111	all		95	135	35	-	25	20	30
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112	all		95	-	35	-	25	20	30
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 14 — Alloy EN AW-3103 [Al Mn1]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	all	95	-	35	-	25	20	28
O, H111	all	all	95	135	35	-	25	20	28
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		95	-	35	-	25	20	28
O, H111	all		95	135	35	-	25	20	28
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		95	-	35	-	25	20	28
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 15 — Alloy EN AW-5005 [Al Mg1(B)] and Alloy EN AW-5005A [Al Mg1(C)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	all	100	100	-	40	-	18	16	30
O, H111	≤ 80	≤ 60	100	150	40	-	18	16	30
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		100	-	40	-	18	16	30
O, H111	≤ 20		100	150	40	-	20	18	30
Extruded Profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	all		100	-	40	-	18	16	30
O, H111	≤ 20		100	150	40	-	20	18	30
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 16 — Alloy EN AW-5019 [Al Mg5]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 200	≤ 200	250	-	110	-	14	12	65
O, H111	≤ 200	≤ 200	250	320	110	-	15	13	65
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 30		250	-	110	-	14	12	65
O, H111	≤ 30		250	320	110	-	15	13	65
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 30		250	-	110	-	14	12	65
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 21 — Alloy EN AW-5154A [Al Mg3,5(A)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 200	≤ 200	200	-	85	-	16	14	55
O, H111	≤ 200	≤ 200	200	275	85	-	18	16	55
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 25		200	-	85	-	16	14	55
O, H111	≤ 25		200	275	85	-	18	16	55
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 25		200	-	85	-	16	14	55
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 22 — Alloy EN AW-5454 [Al Mg3Mn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 200	≤ 200	200	-	85	-	16	14	60
O, H111	≤ 200	≤ 200	200	275	85	-	18	16	60
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 25		200	-	85	-	16	14	60
O, H111	≤ 25		200	275	85	-	18	16	60
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 25		200	-	85	-	16	14	60
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 23 — Alloy EN AW-5754 [Al Mg3]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
F ^c , H112	≤ 150	≤ 150	180	-	80	-	14	12	47
	$150 < D \leq 250$	$150 < S \leq 250$	180	-	70	-	13	-	47
O, H111	≤ 150	≤ 150	180	250	80	-	17	15	45
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112		≤ 25	180	-	80	-	14	12	47
O, H111		≤ 25	180	250	80	-	17	15	45
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
F ^c , H112		≤ 25	180	-	80	-	14	12	47
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 24 — Alloy EN AW-5083 [Al Mg4,5Mn0,7]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
F ^c	≤ 200	≤ 200	270	-	110	-	12	10	70
	$200 < D \leq 250$	$200 < S \leq 250$	260	-	100	-	12	-	70
O, H111	≤ 200	≤ 200	270	-	110	-	12	10	70
H112	≤ 200	≤ 200	270	-	125	-	12	10	70
Extruded tube									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
F ^c		all	270	-	110	-	12	10	70
O, H111		all	270	-	110	-	12	10	70
H112		all	270	-	125	-	12	10	70
Extruded profile									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
F ^c		all	270	-	110	-	12	10	70
H112		all	270	-	125	-	12	10	70
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 25 — Alloy EN AW-5086 [Al Mg4]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
F ^c , H112	≤ 250	≤ 250	240	-	95	-	12	10	65
O, H111	≤ 200	≤ 200	240	320	95	-	18	15	65
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112	all		240	-	95	-	12	10	65
O, H111	all		240	320	95	-	18	15	65
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.			
F ^c , H112	all		240	-	95	-	12	10	65
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c F Temper: property values are for information only.									

Table 26 — Alloy EN AW-6101A [Al MgSi(A)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 150	≤ 150	200	-	170	-	10	8	70
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 25		200	-	170	-	10	8	70
Extruded profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 50		200	-	170	-	10	8	70
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 27 — Alloy EN AW-6101B [Al MgSi(B)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^{c d}	-	≤ 15	215	-	160	-	8	6	70
T7 ^{c e}	-	≤ 15	170	-	120	-	12	10	60
Extruded tube									
Temper	Wall thickness t mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW	
		min.	max.	min.	max.	min.	min.		
T6 ^{c d}	≤ 15	215	-	160	-	8	6	70	
T7 ^{c e}	≤ 15	170	-	120	-	12	10	60	
Extruded profile									
Temper	Wall thickness t mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW	
		min.	max.	min.	max.	min.	min.		
T6 ^{c d}	≤ 15	215	-	160	-	8	6	70	
T7 ^{c e}	≤ 15	170	-	120	-	12	10	60	
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d Electrical conductivity $\gamma \geq 30$ MS/m.									
^e Electrical conductivity $\gamma \geq 32$ MS/m.									

Table 28 — Alloy EN AW-6005 [Al SiMg] and Alloy EN AW-6005A [Al SiMg(A)]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 25	≤ 25	270	-	225	-	10	8	90
	$25 < D \leq 50$	$25 < S \leq 50$	270	-	225	-	8	-	90
	$50 < D \leq 100$	$50 < S \leq 100$	260	-	215	-	8	-	85
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 5	270	-	225	-	8	6	90
		$5 < t \leq 10$	260	-	215	-	8	6	85
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
<i>Open profile</i> T4 ^c		≤ 25	180	-	90	-	15	13	50
<i>Open profile</i> T6 ^c		≤ 5	270	-	225	-	8	6	90
		$5 < t \leq 10$	260	-	215	-	8	6	85
		$10 < t \leq 25$	250	-	200	-	8	6	85
<i>Hollow profile</i> T4 ^c		≤ 10	180	-	90	-	15	13	50
<i>Hollow profile</i> T6 ^c		≤ 5	255	-	215	-	8	6	85
		$5 < t \leq 15$	250	-	200	-	8	6	85
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 29 — Alloy EN AW-6106 [Al MgSiMn]

Extruded rod/bar								
Not specified								
Extruded tube								
Not specified								
Extruded profile								
Temper	Wall thickness <i>t</i> mm	<i>R_m</i> MPa		<i>R_{p0,2}</i> MPa		<i>A</i> % min.	<i>A</i> _{50 mm} % min.	Hardness Typical value HBW
		min.	max.	min.	max.			
T6 ^a	≤ 10	250	-	200	-	8	6	75
^a Properties may be obtained by press quenching.								

Table 30 — Alloy EN AW-6008 [Al SiMgV]

Extruded rod/bar								
Not specified								
Extruded tube								
Temper	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t	MPa		MPa		%	%	
	mm	min.	max.	min.	max.	min.	min.	
T4	≤ 10	180	-	90		15	13	50
T6 ^a	≤ 5	270	-	225	-	8	6	90
	$5 < t \leq 10$	260	-	215	-	8	6	85
Extruded profile ^b								
Temper	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t	MPa		MPa		%	%	
	mm	min.	max.	min.	max.	min.	min.	
<i>Open profile</i> T4 ^a	≤ 10	180	-	90	-	15	13	50
<i>Open profile</i> T6 ^a	≤ 5	270	-	225	-	8	6	90
	$5 < t \leq 10$	260	-	215	-	8	6	85
<i>Hollow profile</i> T4 ^a	≤ 10	180	-	90	-	15	13	50
<i>Hollow profile</i> T6 ^a	≤ 5	255	-	215	-	8	6	85
	$5 < t \leq 10$	250	-	200	-	8	6	85
^a Properties may be obtained by press quenching.								
^b If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.								

Table 31— Alloy EN AW-6110A [Al Mg0,9Si0,9MnCu(A)]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T5 ^c	≤ 120	≤ 120	380	-	360	-	10	8	115
T6 ^c	≤ 120	≤ 150	410	-	380	-	10	8	120
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.			
T4 ^c		≤ 25	320		220	-	16	14	85
T6 ^c		≤ 25	380	-	360	-	10	8	120
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.			
T4 ^c		≤ 25	320		220	-	16	14	85
T6 ^c		≤ 25	380	-	360	-	10	8	120
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 32 — Alloy EN AW-6012 [Al MgSiPb]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c	≤ 150	≤ 150	310	-	260	-	8	6	105
	150 < D ≤ 200	150 < S ≤ 200	260	-	200	-	8	-	105
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c		≤ 30	310	-	260	-	8	6	105
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c		≤ 30	310	-	260	-	8	6	105
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 33 — Alloy EN AW-6014 [Al Mg0,6SiV]

Extruded rod/bar								
Not specified								
Extruded tube								
Temper	Wall thickness <i>t</i> mm	<i>R_m</i> MPa		<i>R_{p0,2}</i> MPa		<i>A</i> %	<i>A_{50 mm}</i> %	Hardness
		min.	max.	min.	max.	min.	min.	Typical value HBW
T4 ^a	≤ 10	140		70	-	15	13	55
T6 ^a	≤ 5	250	-	200	-	8	6	80
	5 < <i>t</i> ≤ 10	225	-	180	-	8	6	80
Extruded profile ^b								
Temper	Wall thickness <i>t</i> mm	<i>R_m</i> MPa		<i>R_{p0,2}</i> MPa		<i>A</i> %	<i>A_{50 mm}</i> %	Hardness
		min.	max.	min.	max.	min.	min.	Typical value HBW
Open profile T4 ^a	≤ 10	140	-	70	-	15	13	55
Open profile T6 ^a	≤ 5	250	-	200	-	10	8	80
	5 < <i>t</i> ≤ 10	225	-	180	-	8	6	80
Hollow profile T4 ^a	≤ 10	140	-	70	-	15	13	55
Hollow profile T6 ^a	≤ 5	250	-	200	-	8	6	80
	5 < <i>t</i> ≤ 10	225	-	180	-	8	6	80
^a Properties may be obtained by press quenching.								
^b If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.								

Table 34 — Alloy EN AW-6018 [Al Mg1SiPbMn]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
T6, T6510, T6511 ^c	≤ 150	≤ 150	310	-	260	-	8	6	-
	$150 < D \leq 200$	$150 < S \leq 200$	260	-	200	-	8	-	-
Extruded tube									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
T6, T6510, T6511 ^c		≤ 30	310	-	260	-	8	6	-
Extruded profile									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
T6, T6510, T6511 ^c		≤ 30	310	-	260	-	8	6	-
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 35 — Alloy EN AW-6023 [Al Si1Sn1MgBi]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
T6, T6510, T6511 ^c	≤ 150	≤ 150	320	-	270	-	10	8	-
Extruded tube									
Not specified									
Extruded profile									
Not specified									
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 36 — Alloy EN AW-6026 [Al MgSiBi]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness HBW Typical Value
	D ^a	S ^b	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c	≤ 140	≤ 140	370	-	300	-	8	6	95
	140 < D ≤ 200	140 < S ≤ 200	340	-	250	-	8	6	90
	200 < D ≤ 250	200 < S ≤ 250	300	-	200	-	8	6	90
Extruded tube									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	HBW Typical Value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c	≤ 30		340	-	260	-	8	6	90
Extruded Profile									
Temper	Wall thickness t mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	HBW Typical Value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c	≤ 40		340	-	260	-	8	6	90
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar..									
^c Properties may be obtained by press quenching									

Table 37 — Alloy EN AW-6351 [Al Si1Mg0,5Mn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	160	-	110	14	12	35
T4 ^c	≤ 200	≤ 200	205	-	110	-	14	12	67
T6 ^c	≤ 20	≤ 20	295	-	250	-	8	6	95
	$20 < D \leq 75$	$20 < S \leq 75$	300	-	255	-	8	-	95
	$75 < D \leq 150$	$75 < S \leq 150$	310	-	260	-	8	-	95
	$150 < D \leq 200$	$150 < S \leq 200$	280	-	240	-	6	-	95
	$200 < D \leq 250$	$200 < S \leq 250$	270	-	200	-	6	-	95
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 25	-	160	-	110	14	12	35
T4 ^c		≤ 25	205	-	110	-	14	12	67
T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 25$	300	-	255	-	10	8	95
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
O, H111		all	-	160	-	110	14	12	35
T4 ^c		≤ 25	205	-	110	-	14	12	67
Open profile T5		≤ 5	270	-	230	-	8	6	90
Open profile T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 25$	300	-	255	-	10	8	95
Hollow profile T5		≤ 5	270	-	230	-	8	6	90
Hollow profile T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 25$	300	-	255	-	10	8	95
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 38 — Alloy EN AW-6056 [Al Si1MgCuMn]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4, T451, T4511 ^c	≤ 80	≤ 80	350	-	245	-	15	14	95
T6, T651, T6511 ^c	≤ 80	≤ 80	380	-	360	-	10	8	115
T78, T7851, T78511 ^c	≤ 80	≤ 80	360	-	335	-	10	8	105
Extruded profile									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t	mm	min.	max.	min.	max.	%	%	
T4, T4510, T4511 ^c		≤ 10	350	-	245	-	15	14	95
T6, T6510, T6511 ^c		≤ 10	380	-	360	-	10	8	115
T78, T78510, T78511 ^c		≤ 10	360	-	335	-	10	8	105
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 39 — Alloy EN AW-6060 [Al MgSi]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 150	≤ 150	120	-	60	-	16	14	50
T5	≤ 150	≤ 150	160	-	120	-	8	6	60
T6 ^c	≤ 150	≤ 150	190	-	150	-	8	6	70
T64 ^{c d}	≤ 50	≤ 50	180	-	120	-	12	10	60
T66 ^c	≤ 150	≤ 150	215	-	160	-	8	6	75
Extruded tube									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 15		120	-	60	-	16	14	50
T5	≤ 15		160	-	120	-	8	6	60
T6 ^c	≤ 15		190	-	150	-	8	6	70
T64 ^{c d}	≤ 15		180	-	120	-	12	10	60
T66 ^c	≤ 15		215	-	160	-	8	6	75
Extruded profile ^e									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 25		120	-	60	-	16	14	50
T5	≤ 5		160	-	120	-	8	6	60
	5 < t ≤ 25		140	-	100	-	8	6	60
T6 ^c	≤ 5		190	-	150	-	8	6	70
	5 < t ≤ 25		170	-	140	-	8	6	70
T64 ^{c d}	≤ 15		180	-	120	-	12	10	60
T66 ^c	≤ 5		215	-	160	-	8	6	75
	5 < t ≤ 25		195	-	150	-	8	6	75
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d Bending quality.									
^e If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 40 — Alloy EN AW-6360 [Al SiMgMn]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 150	≤ 150	110	-	50	-	16	14	40
T5	≤ 150	≤ 150	150	-	110	-	8	6	50
T6 ^c	≤ 150	≤ 150	185	-	140	-	8	6	60
T66 ^c	≤ 150	≤ 150	195	-	150	-	8	6	65
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T4 ^c		≤ 15	110	-	50	-	16	14	40
T5		≤ 15	150	-	120	-	8	6	50
T6 ^c		≤ 15	185	-	140	-	8	6	60
T66 ^c		≤ 15	195	-	150	-	8	6	65
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T4 ^c		≤ 25	110	-	50	-	16	14	40
T5		≤ 25	150	-	110	-	8	6	50
T6 ^c		≤ 25	185	-	140	-	8	6	60
T66 ^c		≤ 25	195	-	150	-	8	6	65
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 41 — Alloy EN AW-6061 [Al Mg1SiCu]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	150	-	110	16	14	30
T4 ^c	≤ 200	≤ 200	180	-	110	-	15	13	65
T6 ^c	≤ 200	≤ 200	260	-	240	-	8	6	95
Extruded tube									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t	mm	MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 25	-	150	-	110	16	14	30
T4 ^c		≤ 25	180	-	110	-	15	13	65
T6 ^c		≤ 5	260	-	240	-	8	6	95
		5 < t ≤ 25	260	-	240	-	10	8	95
Extruded profile ^d									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	t	mm	MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T4 ^c		≤ 25	180	-	110	-	15	13	65
T6 ^c		≤ 5	260	-	240	-	9	7	95
		5 < t ≤ 25	260	-	240	-	10	8	95
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 42 — Alloy EN AW-6261 [Al Mg1SiCuMn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 100	≤ 100	-	170	-	120	14	12	-
T4 ^c	≤ 100	≤ 100	180	-	100	-	14	12	-
T6 ^c	≤ 20	≤ 20	290	-	245	-	8	7	100
	$20 < D \leq 100$	$20 < S \leq 100$	290	-	245	-	8	-	100
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 10	-	170	-	120	14	12	-
T4 ^c		≤ 10	180	-	100	-	14	12	-
T5		≤ 5	270	-	230	-	8	7	-
		$5 < t \leq 10$	260	-	220	-	9	8	-
T6 ^c		≤ 5	290	-	245	-	8	7	100
		$5 < t \leq 10$	290	-	245	-	9	8	100
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
O, H111		all	-	170	-	120	14	12	-
T4 ^c		≤ 25	180	-	100	-	14	12	-
Open profile T5		≤ 5	270	-	230	-	8	7	-
		$5 < t \leq 25$	260	-	220	-	9	8	-
		> 25	250	-	210	-	9	-	-
Open profile T6 ^c		≤ 5	290	-	245	-	8	7	100
		$5 < t \leq 25$	280	-	235	-	8	7	100
Hollow profile T5		≤ 5	270	-	230	-	8	7	-
		$5 < t \leq 10$	260	-	220	-	9	8	-
Hollow profile T6 ^c		≤ 5	290	-	245	-	8	7	100
		$5 < t \leq 10$	270	-	230	-	9	8	100
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 43 — Alloy EN AW-6262 [Al Mg1SiPb]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
T6 ^c	≤ 200	≤ 200	260	-	240	-	10	8	75
Extruded tube									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min.	Typical value HBW
T6 ^c	≤ 25		260	-	240	-	10	8	75
Extruded profile									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min.	Typical value HBW
T6 ^c	≤ 25		260	-	240	-	10	8	75
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 44 — Alloy EN AW-6262A [Al Mg1SiSn]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
T6 ^c	≤ 220	≤ 155	260	-	240	-	10	8	-
Extruded tube									
Not specified									
Extruded profile									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	t		MPa		MPa		%	%	
	mm		min.	max.	min.	max.	min.	min.	Typical value HBW
T6 ^c	≤ 25		260	-	240	-	10	8	-
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 45 — Alloy EN AW-6063 [Al Mg0,7Si]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
O, H111	≤ 200	≤ 200	-	130	-	-	18	16	25
T4 ^c	≤ 150	≤ 150	130	-	65	-	14	12	50
	$150 < D \leq 200$	$150 < S \leq 200$	120	-	65	-	12	-	50
T5	≤ 200	≤ 200	175	-	130	-	8	6	65
T6 ^c	≤ 150	≤ 150	215	-	170	-	10	8	75
	$150 < D \leq 200$	$150 < S \leq 200$	195	-	160	-	10	-	75
T66 ^c	≤ 200	≤ 200	245	-	200	-	10	8	80
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
O, H111		≤ 25	-	130	-	-	18	16	25
T4 ^c		≤ 10	130	-	65	-	14	12	50
		$10 < t \leq 25$	120	-	65	-	12	10	50
T5		< 25	175	-	130	-	8	6	65
T6 ^c		≤ 25	215	-	170	-	10	8	75
T66 ^c		≤ 25	245	-	200	-	10	8	80
Extruded profile ^e									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T4 ^c		≤ 25	130	-	65	-	14	12	50
T5		≤ 10	175	-	130	-	8	6	65
		$10 < t \leq 25$	160	-	110	-	7	5	65
T6 ^c		≤ 10	215	-	170	-	8	6	75
		$10 < t \leq 25$	195	-	160	-	8	6	75
T64 ^{c d}		≤ 15	180	-	120	-	12	10	65
T66 ^c		≤ 10	245	-	200	-	8	6	80
		$10 < t \leq 25$	225	-	180	-	8	6	80
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d Bending quality.									
^e If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 46 — Alloy EN AW-6063A [Al Mg0,7Si(A)]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	150	-	-	16	14	28
T4 ^c	≤ 150	≤ 150	150	-	90	-	12	10	50
	$150 < D \leq 200$	$150 < S \leq 200$	140	-	90	-	10	-	50
T5	≤ 200	≤ 200	200	-	160	-	7	5	75
T6 ^c	≤ 150	≤ 150	230	-	190	-	7	5	80
	$150 < D \leq 200$	$150 < S \leq 200$	220	-	160	-	7	-	80
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
O, H111		≤ 25	-	150	-	-	16	14	28
T4 ^c		≤ 10	150	-	90	-	12	10	50
		$10 < t \leq 25$	140	-	90	-	10	8	50
T5		≤ 25	200	-	160	-	7	5	75
T6 ^c		≤ 25	230	-	190	-	7	5	80
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T4 ^c		≤ 25	150	-	90	-	12	10	50
T5		≤ 10	200	-	160	-	7	5	75
		$10 < t \leq 25$	190	-	150	-	6	4	75
T6 ^c		≤ 10	230	-	190	-	7	5	80
		$10 < t \leq 25$	220	-	180	-	5	4	80
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 47 — Alloy EN AW-6463 [Al Mg0,7Si(B)]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 150	≤ 150	125	-	75	-	14	12	46
T5	≤ 150	≤ 150	150	-	110	-	8	6	60
T6 ^c	≤ 150	≤ 150	195	-	160	-	10	8	74
Extruded tube									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	t	mm	min.	max.	min.	max.	%	%	Typical value HBW
T6 ^c		≤ 25	195	-	160	-	10	8	74
Extruded profile ^d									
Temper	Wall thickness		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	t	mm	min.	max.	min.	max.	%	%	Typical value HBW
T4 ^c		≤ 50	125	-	75	-	14	12	46
T5		≤ 50	150	-	110	-	8	6	60
T6 ^c		≤ 50	195	-	160	-	10	8	74
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 48 — Alloy EN AW-6064A [Al Mg1SiBi]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c	≤ 140	≤ 140	310	-	260	-	8	6	95
	140 < D ≤ 250	140 < S ≤ 250	260	-	240	-	8	6	90
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c		≤ 30	310	-	260	-	8	6	90
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 ^c		≤ 40	310	-	260	-	8	6	90
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Characteristics may be obtained by tempering under press.									

Table 49 — Alloy EN AW-6065 [Al Mg1Bi1Si]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 220	≤ 155	260	-	240	-	10	8	-
Extruded tube Not specified									
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 25	260	-	240	-	10	8	-
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 50 — Alloy EN AW-6081 [Al Si0,9MgMn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 250	≤ 250	275	-	240	-	8	6	95
Extruded tube									
Temper	Wall thickness t mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW	
		min.	max.	min.	max.	min.	min.		
T6 ^c	≤ 25	275	-	240	-	8	6	95	
Extruded profile									
Temper	Wall thickness t mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW	
		min.	max.	min.	max.	min.	min.		
<i>Open profile</i> T6 ^c	≤ 25	275	-	240	-	8	6	95	
<i>Hollow profile</i> T6 ^c	≤ 15	275	-	240	-	8	6	95	
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 51 — Alloy EN AW-6082 [Al Si1MgMn]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	160	-	110	14	12	35
T4 ^c	≤ 200	≤ 200	205	-	110	-	14	12	70
T6 ^c	≤ 20	≤ 20	295	-	250	-	8	6	95
	$20 < D \leq 150$	$20 < S \leq 150$	310	-	260	-	8	-	95
	$150 < D \leq 200$	$150 < S \leq 200$	280	-	240	-	6	-	95
	$200 < D \leq 250$	$200 < S \leq 250$	270	-	200	-	6	-	95
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			min.	max.	min.	max.	%	%	
O, H111		≤ 25	-	160	-	110	14	12	35
T4 ^c		≤ 25	205	-	110	-	14	12	70
T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 25$	310	-	260	-	10	8	95
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			min.	max.	min.	max.	%	%	
O, H111		all	-	160	-	110	14	12	35
T4 ^c		≤ 25	205	-	110	-	14	12	70
Open profile T5		≤ 5	270	-	230	-	8	6	90
Open profile T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 25$	310	-	260	-	10	8	95
Hollow profile T5		≤ 5	270	-	230	-	8	6	90
Hollow profile T6 ^c		≤ 5	290	-	250	-	8	6	95
		$5 < t \leq 15$	310	-	260	-	10	8	95
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 52 — Alloy EN AW-6182 [Al Si1MgZr]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T4 ^c	≤ 220	≤ 155	205	-	110	-	12	10	-
T6 ^{c, d}	$9 < D \leq 100$	$9 < S \leq 100$	360	-	330	-	9	7	-
	$100 < D \leq 150$	$100 < S \leq 150$	330	-	300	-	8	6	-
	$150 < D \leq 220$	$150 < S \leq 220$	280	-	240	-	6	4	-
Extruded tube Not specified									
Extruded profile Not specified									
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to normal solution heat treatment.									

Table 53 — Alloy EN AW-7003 [Al Zn6Mg0,8Zr]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T5	all	all	310	-	260	-	10	8	-
T6 ^c	≤ 50	≤ 50	350	-	290	-	10	8	110
	$50 < D \leq 150$	$50 < S \leq 150$	340	,	280	-	10	8	110
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T5		all	310	-	260	-	10	8	-
T6 ^c		≤ 10	350	-	290	-	10	8	110
		$10 < t \leq 25$	340	-	280	-	10	8	110
Extruded profile ^d									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T5		all	310	-	260	-	10	8	-
T6 ^c		≤ 10	350	-	290	-	10	8	110
		$10 < t \leq 25$	340	-	280	-	10	8	110
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 54 — Alloy EN AW-7005 [Al Zn4,5Mg1,5Mn]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T6 ^c	≤ 50	≤ 50	350	-	290	-	10	8	110
	50 < D ≤ 200	50 < S ≤ 200	340	-	270	-	10	-	110
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T6 ^c		≤ 15	350	-	290	-	10	8	110
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T6 ^c		≤ 40	350	-	290	-	10	8	110
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 55 — Alloy EN AW-7108 [Al Zn5Mg1Zr]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T6 ^c	≤ 100	≤ 100	310	-	260		10	8	90
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T6 ^c		≤ 20	310	-	260	-	10	8	90
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardness Typical value HBW
			min.	max.	min.	max.			
T6 ^c		≤ 30	310	-	260	-	10	8	90
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 56 — Alloy EN AW-7108A [Al Zn5Mg1Zr(A)]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 200	≤ 200	310	-	260		12	10	90
T66 ^c	≤ 50	≤ 50	350	-	290	-	10	8	105
	50 < D ≤ 200	50 < S ≤ 200	340	-	275	-	10	-	105
Extruded tube									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 20	310	-	260	-	12	10	90
T66 ^c		≤ 20	350	-	290	-	10	8	105
Extruded profile									
Temper	t	Wall thickness mm	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness Typical value HBW
			MPa		MPa		%	%	
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 40	310	-	260	-	12	10	90
T66 ^c		≤ 40	350	-	290	-	10	8	105
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 57 — Alloy EN AW-7020 [Al Zn4,5Mg1]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 50	≤ 50	350	-	290	-	10	8	110
	50 < D ≤ 200	50 < S ≤ 200	340	-	275	-	10	-	110
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 15	350	-	290	-	10	8	110
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 40	350	-	290	-	10	8	110
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 58 — Alloy EN AW-7021 [Al Zn5,5Mg1,5]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6 ^c	≤ 40	≤ 40	410	-	350	-	10	8	120
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 10	410	-	350	-	10	8	120
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6 ^c		≤ 20	410	-	350	-	10	8	120
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 59 — Alloy EN AW-7022 [Al Zn5Mg3Cu]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
	D^a	S^b	min.	max.	min.	max.			
T6, T6510, T6511 ^c	≤ 80	≤ 80	490	-	420	-	7	5	133
	$80 < D \leq 200$	$80 < S \leq 200$	470	-	400	-	7	-	
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
			min.	max.	min.	max.			
T6, T6510, T6511 ^c		≤ 30	490	-	420	-	7	5	133
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A % min.	$A_{50\text{ mm}}$ % min.	Hardnes s Typical value HBW
			min.	max.	min.	max.			
T6, T6510, T6511 ^c		≤ 30	490	-	420	-	7	5	133
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c Properties may be obtained by press quenching.									

Table 60 — Alloy EN AW-7049A [Al Zn8MgCu]

Extruded rod/bar									
Temper	Dimensions mm		R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
	D^a	S^b	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511	≤ 100	≤ 100	610	-	530	-	5	4	170
	$100 < D \leq 125$	$100 < S \leq 125$	560	-	500	-	5	-	170
	$125 < D \leq 150$	$125 < S \leq 150$	520	-	430	-	5	-	170
	$150 < D \leq 180$	$150 < S \leq 180$	450	-	400	-	3	-	170
Extruded tube									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511		≤ 30	610	-	530	-	5	4	170
Extruded profile									
Temper	t	Wall thickness mm	R_m MPa		$R_{p0,2}$ MPa		A %	$A_{50\text{ mm}}$ %	Hardness Typical value HBW
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511		≤ 30	610	-	530	-	5	4	170
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									

Table 61 — EN AW-7075 [Al Zn5,5MgCu]

Extruded rod/bar									
Temper	Dimensions		R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
	mm		MPa		MPa		%	%	
	D^a	S^b	min.	max.	min.	max.	min.	min.	Typical value HBW
O, H111	≤ 200	≤ 200	-	275	-	165	10	8	60
T6, T6510, T6511	≤ 25	≤ 25	540	-	480	-	7	5	150
	$25 < D \leq 100$	$25 < S \leq 100$	560	-	500	-	7	-	150
	$100 < D \leq 150$	$100 < S \leq 150$	550	-	440	-	5	-	150
	$150 < D \leq 200$	$150 < S \leq 200$	440	-	400	-	5	-	150
T73, T73510, T73511 ^c	≤ 25	≤ 25	485	-	420	-	7	5	135
	$25 < D \leq 75$	$25 < S \leq 75$	475	-	405	-	7	-	135
	$75 < D \leq 100$	$75 < S \leq 100$	470	-	390	-	6	-	135
	$100 < D \leq 150$	$100 < S \leq 150$	440	-	360	-	6	-	135
Extruded tube									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
O, H111		≤ 10	-	275	-	165	10	-	60
T6, T6510, T6511		≤ 5	540	-	485	-	8	6	150
		$5 < t \leq 10$	560	-	505	-	7	5	150
		$10 < t \leq 50$	560	-	495	-	6	4	150
T73, T73510, T73511 ^c		≤ 5	470	-	400	-	7	5	135
		$5 < t \leq 25$	485	-	420	-	8	6	135
		$25 < t \leq 50$	475	-	405	-	8	-	135
Extruded profile ^d									
Temper	t	Wall thickness	R_m		$R_{p0,2}$		A	$A_{50\text{ mm}}$	Hardness
			MPa		MPa		%	%	
		mm	min.	max.	min.	max.	min.	min.	Typical value HBW
T6, T6510, T6511		≤ 25	530	-	460	-	6	4	150
		$25 < t \leq 60$	540	-	470	-	6	-	150
T73, T73510, T73511 ^c		≤ 25	485	-	420	-	7	5	135
^a D = Diameter for round bar.									
^b S = Width across flats for square and hexagonal bar, thickness for rectangular bar.									
^c For materials of thickness 20 mm or above, see EN 755-1, with respect to stress corrosion cracking resistance.									
^d If a profile cross section comprises different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Annex A
(informative)

List of tempers used in Tables 1 to 61 (extract of EN 515)

Temper	
Symbol	Definition
F	as fabricated (no mechanical property limits specified)
O	annealed - products achieving the required annealed properties after hot forming processes may be designated as O temper
H111	annealed and slightly strain-hardened (less than H11) during subsequent operations such as stretching or straightening
H112	slightly strain-hardened from working at an elevated temperature or from a limited amount of cold work (mechanical property limits specified), such as stretching or straightening
T3	solution heat-treated, cold worked and naturally aged
T3510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and naturally aged The products receive no further straightening after stretching.
T3511	same as T3510 except that minor straightening is allowed after stretching to comply with standard tolerances
T4	solution heat-treated and naturally aged
T4510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and naturally aged The products receive no further straightening after stretching.
T4511	same as T4510 except that minor straightening is allowed after stretching to comply with standard tolerances
T5	cooled from an elevated temperature shaping process and then artificially aged
T6	solution heat-treated and then artificially aged
T64	solution heat-treated and then artificially aged in underageing conditions (between T6 and T61) to improve formability
T6510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and then artificially aged The products receive no further straightening after stretching.
T6511	same as T6510 except that minor straightening is allowed after stretching to comply with standard tolerances
T66	solution heat-treated and then artificially aged - mechanical property level higher than T6 achieved through special control of the process (6000 series alloys)
T7	solution heat-treated and then artificially overaged
T73	solution heat-treated and then artificially overaged in order to achieve the best stress corrosion resistance
T73510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %)

Temper	
Symbol	Definition
	and then artificially overaged in order to achieve the best stress corrosion resistance The products receive no further straightening after stretching.
T73511	same as T73510 except that minor straightening is allowed after stretching to comply with standard tolerances
T8	solution heat-treated, cold worked and then artificially aged
T8510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and then artificially aged The products receive no further straightening after stretching.
T8511	same as T8510 except that minor straightening is allowed after stretching to comply with standard tolerances

Bibliography

[1] EN 515, *Aluminium and aluminium alloys - Wrought products - Temper designations*

[2] EN 573-3, *Aluminium and aluminium alloys - Chemical composition and form of wrought products - Part 3: Chemical composition and form of products*